

GeoBase GB3030L Product Data

<i>Materials</i>	<i>Test Method</i>	<i>GB3030L GeoBase</i>
Polymer	-	Polypropylene
Construction	-	Extruded

<i>Tensile Properties</i>		
Ultimate Tensile Strength - MD/XMD	ASTM D6637 (lbs/ft) / (kN/m)	2,055 / 30.0
Tensile Strength @ 2% Strain - MD/XMD	ASTM D6637 (lbs/ft) / (kN/m)	719 / 10.5
Tensile Strength @ 5% Strain - MD/XMD	ASTM D6637 (lbs/ft) / (kN/m)	1,439 / 21.0

<i>Structural Integrity</i>		
Junction Efficiency (%)	ASTM D7737 / D6637	93%
Flexural Stiffness (mg-cm)	ASTM D7748	2,000,000 mg-cm
Aperture Stability (m-N/deg)	ASTM D7864	0.75 m-N/deg

<i>Ultraviolet Stability</i>		
UV % Strength Retained @ 500 hrs	ASTM D4355	100%
Carbon Black Content	ASTM D1603	0.5%
Chemical Damage Stability	EPA 9090A	100%

<i>Physical Properties</i>	<i>Units</i>	
Aperture Dimensions - MD/CMD	in / mm	2.6 / 2.6
Minimum Rib Thickness - MD/CMD	in / mm	0.09 / 0.05
Roll Width	ft	12.9
Roll Length	ft	164
Area Per Roll	SQY	235.5
Weight Per Roll	LBS	159

Updated as of January 2021

Disclaimer: This Product Data Sheet is the sole and exclusive property of Geostar Technologies LLC ("Geostar"). The Product Data Sheet shall not be reproduced, disseminated, or otherwise used in any way, except in connection with the purchase of Geostar HP Products (including, but not limited to the HP product line), without the express written consent of Geostar. Geostar assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Geostar disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.